

WHAT IS CLAIMED IS:

Sub A11

An organic light emitting device comprising

- (i) a first electrode;
- (ii) a region comprising a mixture of (1) N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine, and (2) an electron transport material, and which region further optionally comprises an organic luminescent material, and wherein said mixed region is capable of emitting light in response to hole-electron recombination;
- (iii) a second electrode;
- (iv) an optional thermal layer coated on at least one of the first and second electrodes, wherein one of said first and second electrodes is a hole injection anode, and one of said electrodes is an electron injection cathode, and wherein the organic light emitting device further comprises at least one of
 - (v) a hole transport region interposed or situated between the first electrode and the mixed region; and
 - (vi) an electron transport region interposed or situated between the mixed region and the cathode.

2. A device in accordance with **claim 1** wherein there is at least one of (A) the hole transport material comprising the hole transport region (v) is selected from the group consisting of aromatic amines, porphyrins and indolocarbazoles, and wherein (B) the electron transport material comprising the mixed region (ii) or the electron transport of region (vi) is selected from the group consisting of metal oxinoids, stilbenes, triazines, porphyrins, and quinolines.

Sub All
cont

3. A device in accordance with **claim 1** wherein in the mixed region (ii) the electron transport material is a metal oxinoid.

4. A device in accordance with **claim 1** wherein the mixed region comprises from about 20 weight percent to about 80 weight percent of said N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine; and said electron transport component or material is present in an amount of from about 80 weight percent to about 20 weight percent and said electron transport is a metal oxinoid, and wherein the weight percents are based on the total weight of materials comprising the mixed region (ii).

5. A device in accordance with **claim 1** wherein the mixed region comprises from about 35 weight percent to about 65 weight percent of said N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD); and from about 65 weight percent to about 35 weight percent of said electron transport of a metal oxinoid, and wherein the weight percent total thereof is about 100 weight percent.

6. A device in accordance with **claim 3** wherein the metal oxinoid is selected from the group consisting of tris(8-hydroxyquinoline) aluminum (Alq₃) and bis(8-hydroxyquinolato)-(4-phenylphenolato)aluminum (Balq).

7. A device in accordance with **claim 1** wherein the electron transport region (vi) contains Alq₃ or Balq, and said mixed region (ii) contains from about 0.01 weight percent to about 10 weight percent of a fluorescent luminescent material.

Sub A1
cont

8. A device in accordance with **claim 7** wherein the fluorescent material is selected from the group consisting of coumarin, dicyanomethylene pyranes, polymethine, oxabenzanthrane, xanthene, pyrylium, carbostyl, perylene, acridone, quinacridone, rubrene, anthracene, coronene, phenanthrene, pyrene, butadiene, stilbene, lanthanide metal chelate complexes, rare-earth metal chelate complexes, and 4-(dicyanomethylene)-2-l-propyl-6-(1,1,7,7-tetramethyljulolidyl-9-enyl)-4H-pyran.

9. A device in accordance with **claim 7** wherein the fluorescent material is selected from the group consisting of rubrene, N,N'-dimethylquinacridone (DMQ), 10-2-(benzothiazolyl)-2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H, 5H, 11H-(1)benzopyrroprano (6,7,-8-ij) quinolizin-11-one (C545T), and (2-(1,1-dimethylethyl)-6-(2-(2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H,5H-benzo(ij)quinolizin-9-yl)ethenyl)-4H-pyran-4-ylidene) propanedinitrile (DCJTB).

10. A device in accordance with **claim 1** wherein the mixed region comprises from about 3 weight percent to about 30 weight percent of a luminescent material, and wherein the luminescent material is a phosphorescent material.

11. A device in accordance with **claim 10** wherein the phosphorescent material is selected from the group consisting of 2,3,7,8,12,13,17,18-octaethyl-21H,23H-phorpine platinum(II) (PtOEP) and fac tris(2-phenylpyridine)iridium (Ir(ppy)₃).

Sub All
cut

12. A device in accordance with **claim 1** wherein there is at least one of (A) said hole transport region (v) comprising N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD); and (B) said electron transport region (vi) contains an electron transport material, and wherein the electron transport material in the mixed region (ii) and (vi) are similar components.

13. A device in accordance with **claim 1** wherein there is at least one of (A) said hole transport material comprising said hole transport region (v) is dissimilar than said (p-biphenyl)-N,N'-diphenyl benzidine; and (B) wherein said electron transport region (vi) contains an electron transport material, and wherein said electron transport material in the mixed region (ii) and region (vi) are dissimilar.

14. A device in accordance with **claim 1** wherein each of said regions (ii), (v) and (vi) contain from 1 to about 10 layers.

15. A device in accordance with **claim 14** wherein (1) a first layer of said electron transport region is contacting the mixed region, and which first layer comprises a material selected from the group consisting of metal oxinoids and quinolines; and wherein (2) a second layer of the electron transport region is contacting the cathode, and which second layer comprises a material selected from the group consisting of metal oxinoid, phthalocyanine and triazine.

Sub All
cont

16. A device in accordance with **claim 15** wherein said metal oxinoid is tris(8-hydroxyquinoline)aluminum (Alq_3), bis(8-hydroxyquinolato)-(4-phenylphenolato)aluminum (Balq), or a quinoline of 1,4-bis(4-phenylquinolin-2-yl)benzene, 4,4'-bis(4-phenylquinolin-2-yl)-1,1'-biphenyl (TA); and said second layer is a metal oxinoid of tris(8-hydroxyquinoline)aluminum (Alq_3), bis(8-hydroxyquinolato)-(4-phenylphenolato)aluminum (Balq), copper phthalocyanine (CuPc), or a triazine comprising 4,4'-bis-[2-(4,6-diphenyl-1,3,5-triazinyl)]-1,1'-biphenyl, 4,4'-bis-[2-(4,6-di-p-tolyl-1,3,5-triazinyl)]-1,1'-biphenyl, 4,4'-bis-[2-(4,6-di-m-tolyl-1,3,5-triazinyl)]-1,1'-biphenyl, 4,4'-bis-[2-(4,6-di-p-methoxyphenyl-1,3,5-triazinyl)]-1,1'-biphenyl, or 4,4'-bis-[2-(4,6-di-m-methoxyphenyl-1,3,5-triazinyl)]-1,1'-biphenyl, 2,4,6-tris(4-biphenyl)-1,3,5-triazine.

17. A device in accordance with **claim 1** wherein said hole transport region (v) is comprised of at least two layers.

18. A device in accordance with **claim 17** wherein one layer of said hole transport region contacts the anode, and which layer comprises a porphyrin; and (2) a second layer of the hole transport region contacts the mixed region, and which second layer comprises a material selected from the group consisting of tertiary aromatic amines, and indolocarbazoles.

19. A device in accordance with **claim 18** wherein the first layer comprises copper phthalocyanine, and the second layer comprises N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD), 5,11-dinaphthyl-5,11-dihydroindolo[3,2-b]carbazole, or 2,8-dimethyl-5,11-dinaphthyl-5,11-dihydroindolo[3,2-b]carbazole.

1000593 10001

Sub P1
cut

20. A device in accordance with **claim 1** wherein said hole transport region comprises a layer comprised of a mixture of from about 25 weight percent to about 99 weight percent of a porphyrin, and from about 75 weight percent to about 1 weight percent of an aromatic tertiary amine or an indolocarbazole.

21. A device in accordance with **claim 20** wherein said hole transport region includes a layer comprised of a mixture of (i) a porphyrin of copper phthalocyanine (CuPc), and (ii) a tertiary aromatic amine of N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD), or an indolocarbazole of 5,11-di-naphthyl-5,11-dihydroindolo[3,2-b]carbazole, or 2,8-dimethyl-5,11-di-naphthyl-5,11-dihydroindolo[3,2-b]carbazole.

22. A device in accordance with **claim 1** wherein there is at least one of (A) said anode, which anode is optionally indium-tin-oxide, and (B) said cathode is selected from the group consisting of (i) a layer comprised of Mg and Ag; (ii) a layer comprised of Al; (iii) a layer comprised of indium-tin-oxide; or (iv) a layer comprised of (1) an organic compound, (2) Mg, and (3) Ag.

23. A device in accordance with **claim 22** wherein the cathode further comprises an alkaline metal or a compound thereof.

24. A device in accordance with **claim 23** wherein the alkaline metal is selected from the group consisting of Li, Na, K and Cs.

SubA11
cont

25. A device in accordance with **claim 1** wherein said thermal protective element is present and is comprised of a layer of SiO, SiO₂ or mixtures thereof.

26. A device in accordance with **claim 1** wherein the mixed region (ii) has a thickness of from about 5 nanometers to about 500 nanometers; the hole transport region (v) has a thickness of from about 5 nanometers to about 250 nanometers; and the electron transport region (vi) has a thickness of from about 5 nanometers to about 100 nanometers.

1000593-110001
F03011-265001

SubALL
cont

27. A device in accordance with **claim 1** and comprising
- (i) an anode of indium-tin-oxide with a thickness of from about 30 to about 300 nanometers coated on a substrate, the anode and the substrate being capable of transmitting at least about 70 percent of radiation of a wavelength of from about 400 nanometers to about 750 nanometers;
 - (ii) a hole transport region situated on the anode comprised of a material selected from the group consisting of copper phthalocyanine (CuPc), N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD), 5,11-di-naphthyl-5,11-dihydroindolo[3,2-b]carbazole, and 2,8-dimethyl-5,11-di-naphthyl-5,11-dihydroindolo[3,2-b]carbazole; and which region has a thickness of from about 5 nanometers to about 100 nanometers;
 - (iii) a mixed region situated on the hole transport region comprised of from about 35 weight percent to about 65 weight percent of N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD), and from about 65 weight percent to about 35 weight percent of tris(8-hydroxyquinoline) aluminum or bis(8-hydroxyquinolato)-(4-phenylphenolato) aluminum, wherein all weight percents are based on the total weight of materials comprising the mixed region, and wherein the thickness of the mixed region is from about 20 nanometers to about 200 nanometers;
 - (iv) an electron transport region situated on the mixed region comprised of tris(8-hydroxyquinoline) aluminum (Alq₃) or bis(8-hydroxyquinolato)-(4-phenylphenolato)aluminum (Ba1q) wherein the thickness of the electron transport region is from about 5 nanometers to about 50 nanometers;
 - (v) a cathode situated on the electron transport region comprised of one of a layer comprising (1) an Mg:Ag alloy or Al of a thickness of from about 50 nanometers to about 500 nanometers; and (2)

1000593-1.0301

1000599-10301

Sub All
cont 11

from about 40 volume percent to about 55 percent of Mg; from about 2 volume percent to about 10 volume percent of Ag; and from about 55 volume percent to about 40 volume percent of Alq_3 , wherein the thickness of the first layer is from about 100 nanometers to about 600 nanometers coated with said layers with a thickness of from about 50 nanometers to about 500 nanometers comprising a metal or a metal alloy; and

(vi) a thermal protective layer situated on the cathode comprised of SiO , SiO_2 or mixtures thereof of a thickness of from about 100 nanometers to about 1,000 nanometers.

Sub All
cont'd

28. A device in accordance with **claim 27** wherein the mixed region further comprises one of

(i) about 0.2 weight percent to about 2 weight percent of a luminescent material selected from the group consisting of rubrene, N,N'-dimethylquinacridone (DMQ), and 10-2-(benzothiazolyl)-2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H, 5H, 11H-(1)benzopyrroprano (6,7,-8-ij) quinolizin-11-one (C545T);

(ii) about 0.2 weight percent to about 5 weight percent of (2-(1,1-dimethylethyl)-6-(2-(2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H,5H-benzo(ij)quinolizin-9-yl)ethenyl)-4H-pyran-4-ylidene) propanedinitrile (DCJTB); and

(iii) about 5 weight percent to about 25 weight percent of 2,3,7,8,12,13,17,18-octaethyl-21H,23H-phorpine platinum(II) (PtOEP).

10005593.10807
T0807.1.645007

Sub All
cont'd

29. A device in accordance with **claim 1** and comprising
- (i) an anode of indium-tin-oxide with a thickness of from about 30 to about 300 nanometers coated on a substrate;
 - (ii) a hole transport region in contact with said anode comprised of a compound selected from the group consisting of N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD), 5,11-di-naphthyl-5,11-dihydroindolo[3,2-b]carbazole, and 2,8-dimethyl-5,11-di-naphthyl-5,11-dihydroindolo[3,2-b]carbazole; and which region further comprises a buffer layer contacting the anode, and which buffer layer is comprised of copper phthalocyanine, wherein the thickness of the buffer layer is from about 10 nanometers to about 30 nanometers, and the thickness of the hole transport region is from about 5 nanometers to about 20 nanometers greater than the thickness of the buffer layer;
 - (iii) a mixed region situated on the hole transport region comprised of from about 35 weight percent to about 65 weight percent of N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD) and from about 65 weight percent to about 35 weight percent of tris(8-hydroxyquinoline)aluminum or bis(8-hydroxyquinolato)-(4-phenylphenolato) aluminum, wherein all weight percents are based on the total weight of materials comprising the mixed region, and wherein the thickness of the mixed region is from about 20 nanometers to about 200 nanometers;
 - (iv) an electron transport region situated on the mixed region comprised of tris(8-hydroxyquinoline)aluminum (Alq₃) or bis(8-hydroxyquinolato)-(4-phenylphenolato)aluminum (Balq), wherein the thickness of the electron transport region is from about 5 nanometers to about 50 nanometers;
 - (v) a cathode situated on the electron transport region comprised of one of (1) a first layer comprised of Mg:Ag alloy or Al of a thickness of from about 50 nanometers to about 500 nanometers; and (2)

Sub All
cont 1

a second layer comprised of from about 40 volume percent to about 55 volume percent of Mg; from about 2 volume percent to about 10 volume percent of Ag; and from about 55 volume percent to about 40 volume percent of Alq₃, wherein the thickness of the first layer is from about 100 nanometers to about 600 nanometers; and the second layer of thickness is from about 50 nanometers to about 500 nanometers and comprises a metal or a metal alloy; and

(vi) a thermal protective layer situated on the cathode comprised of SiO, SiO₂ or mixtures thereof of a thickness of from about 100 nanometers to about 1,000 nanometers.

30. A device in accordance with **claim 29** wherein the mixed region further comprises one of

(i) from about 0.2 weight percent to about 2 weight percent of a luminescent material selected from the group consisting of rubrene, N,N'-dimethylquinacridone (DMQ), and 10-2-(benzothiazolyl)-2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H, 5H, 11H-(1)benzopyrroprano (6,7,-8-ij) quinolizin-11-one (C545T);

(ii) from about 0.2 weight percent to about 5 weight percent of (2-(1,1-dimethylethyl)-6-(2-(2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H,5H-benzo(ij)quinolizin-9-yl)ethenyl)-4H-pyran-4-ylidene) propanedinitrile (DCJTB), and

(iii) from about 5 weight percent to about 25 weight percent of 2,3,7,8,12,13,17,18-octaethyl-21H,23H-phorpine platinum(II) (PtOEP).

1000593 110801

Sub All
part 1

31. A device in accordance with **claim 1** and comprising
- (i) an anode of indium-tin-oxide with a thickness of from about 50 to about 300 nanometers coated on a substrate, the anode and the substrate being capable of transmitting at least about 70 percent of radiation of wavelength of from about 400 nanometers to about 750 nanometers;
 - (ii) a hole transport region situated on the anode comprised of at least one material selected from the group consisting of copper phthalocyanine (CuPc), N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD), 5,11-di-naphthyl-5,11-dihydroindolo[3,2-b]carbazole, and 2,8-dimethyl-5,11-di-naphthyl-5,11-dihydroindolo[3,2-b]carbazole; and which region has a thickness of from about 5 nanometers to about 100 nanometers;
 - (iii) a mixed region situated on the hole transport region comprised of from about 35 weight percent to about 65 weight percent of N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD) and from about 65 weight percent to about 35 weight percent of tris(8-hydroxyquinoline)aluminum or bis(8-hydroxyquinolato)-(4-phenylphenolato) aluminum; and wherein the thickness of the mixed region is from about 20 nanometers to about 200 nanometers;
 - (iv) an electron transport region situated on the mixed region comprising (1) a first layer of thickness from about 5 nanometers to about 25 nanometers contacting the mixed region, wherein this first layer is comprised of a material selected from the group consisting of tris(8-hydroxyquinoline)aluminum (Alq₃), bis(8-hydroxyquinolato)-(4-phenylphenolato)aluminum (Balq), and 1,4-bis(4-phenylquinolin-2-yl)benzene, 4,4'-bis(4-phenylquinolin-2-yl)-1,1'-biphenyl (TA); and (2) a second layer of a thickness of from about 5 nanometers to about 25 nanometers contacting the cathode, wherein the second layer is comprised

Sub All sent 12
of a material selected from the group consisting of tris(8-hydroxyquinoline) aluminum (Alq_3), bis(8-hydroxyquinolato)-(4-phenylphenolato)aluminum (Baq), copper phthalocyanine (CuPc), 4,4'-bis-[2-(4,6-diphenyl-1,3,5-triazinyl)]-1,1'-biphenyl, 4,4'-bis-[2-(4,6-di-p-tolyl-1,3,5-triazinyl)]-1,1'-biphenyl, 4,4'-bis-[2-(4,6-di-m-tolyl-1,3,5-triazinyl)]-1,1'-biphenyl, 4,4'-bis-[2-(4,6-di-p-methoxyphenyl-1,3,5-triazinyl)]-1,1'-biphenyl, 4,4'-bis-[2-(4,6-di-m-methoxyphenyl-1,3,5-triazinyl)]-1,1'-biphenyl, and 2,4,6-tris(4-biphenyl)-1,3,5-triazine;

(v) a cathode situated on the electron transport region comprised of one of (1) a layer comprised of Mg:Ag alloy or Al of a thickness of from about 50 nanometers to about 500 nanometers; and (2) a first layer comprised of from about 40 volume percent to about 55 volume percent of Mg; from about 2 volume percent to about 10 volume percent of Ag; and from about 55 volume percent to about 40 volume percent of Alq_3 , wherein the thickness of the first layer is from about 100 nanometers to about 600 nanometers, and coated with a second layer of a thickness of from about 50 nanometers to about 500 nanometers comprising a metal or a metal alloy; and

(vi) a thermal protective layer situated on the cathode comprised of SiO , SiO_2 or mixtures thereof of a thickness of from about 100 nanometers to about 1,000 nanometers.

1949 1950 1951 1952 1953 1954 1955 1956 1957 1958 1959 1960 1961 1962 1963 1964 1965 1966 1967 1968 1969 1970 1971 1972 1973 1974 1975 1976 1977 1978 1979 1980 1981 1982 1983 1984 1985 1986 1987 1988 1989 1990 1991 1992 1993 1994 1995 1996 1997 1998 1999 2000 2001 2002 2003 2004 2005 2006 2007 2008 2009 2010 2011 2012 2013 2014 2015 2016 2017 2018 2019 2020 2021 2022 2023 2024 2025 2026 2027 2028 2029 2030 2031 2032 2033 2034 2035 2036 2037 2038 2039 2040 2041 2042 2043 2044 2045 2046 2047 2048 2049 2050 2051 2052 2053 2054 2055 2056 2057 2058 2059 2060 2061 2062 2063 2064 2065 2066 2067 2068 2069 2070 2071 2072 2073 2074 2075 2076 2077 2078 2079 2080 2081 2082 2083 2084 2085 2086 2087 2088 2089 2090 2091 2092 2093 2094 2095 2096 2097 2098 2099 2100 2101 2102 2103 2104 2105 2106 2107 2108 2109 2110 2111 2112 2113 2114 2115 2116 2117 2118 2119 2120 2121 2122 2123 2124 2125 2126 2127 2128 2129 2130 2131 2132 2133 2134 2135 2136 2137 2138 2139 2140 2141 2142 2143 2144 2145 2146 2147 2148 2149 2150 2151 2152 2153 2154 2155 2156 2157 2158 2159 2160 2161 2162 2163 2164 2165 2166 2167 2168 2169 2170 2171 2172 2173 2174 2175 2176 2177 2178 2179 2180 2181 2182 2183 2184 2185 2186 2187 2188 2189 2190 2191 2192 2193 2194 2195 2196 2197 2198 2199 2200 2201 2202 2203 2204 2205 2206 2207 2208 2209 2210 2211 2212 2213 2214 2215 2216 2217 2218 2219 2220 2221 2222 2223 2224 2225 2226 2227 2228 2229 2230 2231 2232 2233 2234 2235 2236 2237 2238 2239 2240 2241 2242 2243 2244 2245 2246 2247 2248 2249 2250 2251 2252 2253 2254 2255 2256 2257 2258 2259 2260 2261 2262 2263 2264 2265 2266 2267 2268 2269 2270 2271 2272 2273 2274 2275 2276 2277 2278 2279 2280 2281 2282 2283 2284 2285 2286 2287 2288 2289 2290 2291 2292 2293 2294 2295 2296 2297 2298 2299 2300 2301 2302 2303 2304 2305 2306 2307 2308 2309 2310 2311 2312 2313 2314 2315 2316 2317 2318 2319 2320 2321 2322 2323 2324 2325 2326 2327 2328 2329 2330 2331 2332 2333 2334 2335 2336 2337 2338 2339 2340 2341 2342 2343 2344 2345 2346 2347 2348 2349 2350 2351 2352 2353 2354 2355 2356 2357 2358 2359 2360 2361 2362 2363 2364 2365 2366 2367 2368 2369 2370 2371 2372 2373 2374 2375 2376 2377 2378 2379 2380 2381 2382 2383 2384 2385 2386 2387 2388 2389 2390 2391 2392 2393 2394 2395 2396 2397 2398 2399 2400 2401 2402 2403 2404 2405 2406 2407 2408 2409 2410 2411 2412 2413 2414 2415 2416 2417 2418 2419 2420 2421 2422 2423 2424 2425 2426 2427 2428 2429 2430 2431 2432 2433 2434 2435 2436 2437 2438 2439 2440 2441 2442 2443 2444 2445 2446 2447 2448 2449 2450 2451 2452 2453 2454 2455 2456 2457 2458 2459 2460 2461 2462 2463 2464 2465 2466 2467 2468 2469 2470 2471 2472 2473 2474 2475 2476 2477 2478 2479 2480 2481 2482 2483 2484 2485 2486 2487 2488 2489 2490 2491 2492 2493 2494 2495 2496 2497 2498 2499 2500 2501 2502 2503 2504 2505 2506 2507 2508 2509 2510 2511 2512 2513 2514 2515 2516 2517 2518 2519 2520 2521 2522 2523 2524 2525 2526 2527 2528 2529 2530 2531 2532 2533 2534 2535 2536 2537 2538 2539 2540 2541 2542 2543 2544 2545 2546 2547 2548 2549 2550 2551 2552 2553 2554 2555 2556 2557 2558 2559 2560 2561 2562 2563 2564 2565 2566 2567 2568 2569 2570 2571 2572 2573 2574 2575 2576 2577 2578 2579 2580 2581 2582 2583 2584 2585 2586 2587 2588 2589 2590 2591 2592 2593 2594 2595 2596 2597 2598 2599 2600 2601 2602 2603 2604 2605 2606 2607 2608 2609 2610 2611 2612 2613 2614 2615 2616 2617 2618 2619 2620 2621 2622 2623 2624 2625 2626 2627 2628 2629 2630 2631 2632 2633 2634 2635 2636 2637 2638 2639 2640 2641 2642 2643 2644 2645 2646 2647 2648 2649 2650 2651 2652 2653 2654 2655 2656 2657 2658 2659 2660 2661 2662 2663 2664 2665 2666 2667 2668 2669 2670 2671 2672 2673 2674 2675 2676 2677 2678 2679 2680 2681 2682 2683 2684 2685 2686 2687 2688 2689 2690 2691 2692 2693 2694 2695 2696 2697 2698 2699 2700 2701 2702 2703 2704 2705 2706 2707 2708 2709 2710 2711 2712 2713 2714 2715 2716 2717 2718 2719 2720 2721 2722 2723 2724 2725 2726 2727 2728 2729 2730 2731 2732 2733 2734 2735 2736 2737 2738 2739 2740 2741 2742 2743 2744 2745 2746 2747 2748 2749 2750 2751 2752 2753 2754 2755 2756 2757 2758 2759 2760 2761 2762 2763 2764 2765 2766 2

- (i) from about 0.2 weight percent to about 2 weight percent of a luminescent material selected from the group consisting of rubrene, N,N'-dimethylquinacridone (DMQ), and 10-2-(benzothiazolyl)-2,3,6,7-tetrahydro-1,1,7,7-tetramethyl-1H, 5H, 11H-(1)benzopyrroprano (6,7,-8-ij) quinolizin-11-one (C545T);

- (iii) ~~from about 5 weight percent to about 25 weight percent of 2,3,7,8,12,13,17,18-octaethyl-21H,23H-phorphine platinum(II) (PtOEP.~~

- 63-

Sub A1
cont

34. A device in accordance with **claim 1** and comprising in sequence

- (i) said first electrode;
- (ii) said mixed region with from about 1 to about 3 layers comprising a mixture of (1) N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine (biphenyl TPD), and (2) an electron transport component, and which mixed region further comprises an organic luminescent material;
- (iii) said second electrode;
- (iv) a thermal protective layer coated on one of the first and second electrodes wherein one of said first and second electrodes is a hole injection anode, and one of said electrodes is an electron injection cathode, and wherein the organic light emitting device further comprises at least one of
 - (v) a hole transport region positioned between the first electrode and the mixed region; and
 - (vi) an electron transport region positioned between the mixed region and the cathode.

35. A device in accordance with **claim 34** wherein the mixed region emits light in response to hole electron recombination.

36. A device in accordance with **claim 1** further including a buffer layer in said hole transport region (v).

37. A device in accordance with **claim 1** wherein said protective layer is present, and which device further contains a buffer layer.

38. A device in accordance with **claim 1** wherein each of said regions contains from 1 to about 5 layers.

Sub All
cont

39. A device in accordance with **claim 1** wherein each of said regions contains from about 2 to about 4 layers.

40. A device in accordance with **claim 1** wherein said electron transport of (ii) also functions as a luminescent material or a light emitter.

41. A device in accordance with **claim 1** wherein a luminescent component is further contained in the mixed region, and wherein said electron transport is free of functioning as an emitter.

1000593 110801

Sub All
Cent 12

42.

A device comprising

- (i) a first electrode;
- (ii) a region comprising a mixture of (1) N,N'-bis(p-biphenyl)-N,N'-diphenyl benzidine, and (2) an electron transport material, and which region further optionally comprises an organic luminescent material,
- (iii) a second electrode;
- (iv) an optional thermal layer coated on at least one of the first and second electrodes, wherein one of said first and second electrodes is a hole injection anode, and one of said electrodes is an electron injection cathode, and wherein the organic light emitting device further comprises at least one of
 - (v) a hole transport region interposed or situated between the first electrode and the mixed region; and
 - (vi) an electron transport region interposed or situated between the mixed region and the cathode, and wherein said device contains in said region (ii) a luminescent component wherein said electron transport material also functions as a luminescent component, or wherein said region (ii) is free of a luminescence component where said electron transport component also functions as a luminescent component.